



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B32B 27/32, C08L 23/06, 23/10, C08J 5/18	A1	(11) International Publication Number: WO 98/14327 (43) International Publication Date: 9 April 1998 (09.04.98)
(21) International Application Number: PCT/IB97/01182 (22) International Filing Date: 29 September 1997 (29.09.97) (30) Priority Data: 9620651.1 2 October 1996 (02.10.96) GB (71) Applicant (for all designated States except US): ELOPAK SYSTEMS AG [CH/CH]; Cherstrasse 4, Postfach, CH-8152 Glattbrugg (CH). (72) Inventors; and (75) Inventors/Applicants (for US only): WILSON, Craig, Andrew [GB/FR]; 68, rue du Gaïac, F-76230 Bois-Guillaume (FR). FLOM, Atle [NO/FR]; 66, allée Fleming, F-76230 Bois-Guillaume (FR). (74) Agent: BURROWS, Anthony, Gregory; Business Centre West, Avenue One, Business Park, Letchworth Garden City, Hertfordshire SG6 2HB (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: POLYOLEFIN FILMS AND LAMINATES (57) Abstract <p>By blending a first polyolefin, or an interpolymer thereof, which is of low melt index and is multi-modal in molecular weight distribution, with a homogeneous polyolefin which is compatible in melt mergibility with the first polyolefin, and co-extruding or extruding through a flat slot die the blend, with or without a second polyolefin, or an interpolymer thereof, a laminate or a monolayer is obtained. The laminate comprises a structural layer comprised of the first polyolefin, or the interpolymer thereof, and a sealant layer comprised of the second polyolefin or the interpolymer thereof, having a seal-initiation temperature lower than the seal initiation temperature, or at least the thermoforming temperature plateau, of the structural layer and compatible in melt mergibility with the structural layer. The monolayer or the laminate is particularly suitable for thermoforming into containers.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

POLYOLEFIN FILMS AND LAMINATES

5 This invention relates to one or more layers, to a method of producing the same and to a method of using the same. The invention is concerned particularly, but not exclusively, with one or more layers in the form of a web suitable for thermoforming, especially a packaging laminate to be thermoformed.

10 There are generally used in thermoforming systems for sheet-form packaging material, substances such as polypropylene (PP), polystyrene (PS), polyester and combinations thereof.

15 Known sheet thermoforming systems include tray-forming systems in which a single sheet is formed using heat and pressure and/or vacuum; these tray-forming systems include systems in which the tray is formed on a form-fill-seal (FFS) machine. Other systems are those in which two sheets (which may be two separate webs or a single web folded upon itself) are thermoformed in a mould and sealed together around
20 outlines of the containers, or sealed around the outlines and then thermoformed in the mould.

It is also known to employ a homogeneous polyolefin to modify properties of sealant layers. For example, WO-A-95/21743 discloses a multilayer film, of a thickness of
25 between 40 and 130 microns, and a pouch containing a flowable material. The multilayer film is made from two layers of a sealant film with an interposed layer of a polyethylene. The sealant film is made from a material comprising 10 to 100 parts by weight of a copolymer of ethylene and at least one
30 C₄-C₁₀ alpha-olefin manufactured in a polymerization process using a single-site polymerization catalyst and from 0 to 90 parts by weight of at least one polymer selected from the group consisting of a linear copolymer of ethylene and at least one C₄-C₁₀ alpha-olefin having a density of from 0.900
35 to 0.930 g/cm³ and a melt index of from 0.3 to 2.0, a high-pressure polyethylene having a density of from 0.916 to 0.930 g/cm³ and a melt index of from about 1 to 10, and blends thereof. The polyethylene of the interposed layer is a high density polyethylene with a density of at least 0.930 g/cm³

and a melt index of less than 5. The pouch is made from the multilayer film and has transversely sealed ends. The pouches are particularly useful in the packaging of flowable materials e.g. milk, especially using a vertical form, fill and seal apparatus.

High density polyethylene (HDPE) as generally used in extrusion of film, which is not subsequently to be thermoformed, is typically of Type III or IV, Categories 4 and 5, as defined in ASTM (American Society for Testing and Materials) D1248-84. It is known to increase the melt strength of the HDPE by increasing the average molecular weight.

HDPE as generally used in sheet extrusion for subsequent thermoforming is typically of Type III or IV, Category 3 (ASTM D1248-84). Such HDPE has poor thermoforming characteristics and, on blow-thermoforming machines in which two HDPE strips are brought together and blow-thermoformed, has poor sealing characteristics. Its poor thermoforming characteristics arise from its low melt strength - the portion of the visco-elastic plateau which is suitable for thermoforming is narrower than is desirable. Its poor sealing characteristics arise from its having a seal-initiation temperature which is above its thermoforming temperature plateau and its having a low melt strength at its sealing temperature, such that the sealing pressure of sealing jaws, for example, causes them to penetrate through the HDPE. The softening of the HDPE at its sealing temperature results in great difficulty in transporting such strip through the machine without elongation or other deformation of the strip.

Attempts have been made to improve the thermoforming characteristics of sheet HDPE by increasing the melt strength through increasing the average molecular weight. However this has been found to lead to an increase in thermal retraction [as defined in NF (Norme Française Enregistrée) T54-105, April 1973, condition 130°C] actually worsening the thermoforming characteristics.

However, HDPE is desirable as a packaging substance for a number of reasons, for example because it is readily acceptable in recycling schemes and waste disposal systems,

is readily available and inexpensive, and is relatively light in specific weight.

According to a first aspect of the present invention, there is provided a method comprising providing a laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt
5
10
mergibility with said structural layer, having a seal-initiation temperature lower than that of said structural layer and comprised of a second polyolefin, or an interpolymer thereof, and thermoforming said laminate.

According to a second aspect of the present invention, there is provided a method comprising providing a laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt
15
20
mergibility with said structural layer, having a seal-initiation temperature lower than the thermoforming temperature plateau of said structural layer and comprised of a second polyolefin, or an interpolymer thereof, and thermoforming said laminate.

In relation to these two aspects of the invention, we have surprisingly found that a laminate similar to laminates known as films can be manufactured of sheet thickness
25
suitable for thermoforming. The advantage of using the first polyolefin or the interpolymer thereof, as set out above, is that it thermoforms well, so that it is possible to form
30
containers, e.g. trays, with very high barrier to transmission of water vapour as well as good hot fill capabilities. The inclusion of the sealant layer has the advantage that the processing on FFS machines is significantly improved.

According to a third aspect of the present invention, there is provided a method comprising co-extruding through a flat slot die a first polyolefin, or an interpolymer thereof, which is of low melt index and is multi-modal in molecular weight distribution, and a second polyolefin, or an
35

interpolymer thereof, to provide a laminate comprising a structural layer comprised of said first polyolefin, or said interpolymer thereof, and a sealant layer comprised of said second polyolefin or said interpolymer thereof, having a seal-initiation temperature lower than that of said structural layer and compatible in melt mergibility with said structural layer.

According to a fourth aspect of the present invention, there is provided a method comprising co-extruding through a flat slot die a first polyolefin, or an interpolymer thereof, which is of low melt index and is multi-modal in molecular weight distribution, and a second polyolefin, or an interpolymer thereof, to provide a laminate comprising a structural layer comprised of said first polyolefin, or said interpolymer thereof, and a sealant layer comprised of said second polyolefin or said interpolymer thereof, having a seal-initiation temperature lower than the thermoforming temperature plateau of said structural layer and compatible in melt mergibility with said structural layer.

Owing to these two aspects of the invention, it is possible to produce a laminate by co-extrusion which does not require an adhesive layer between the structural layer and the sealant layer, so simplifying the production process. Moreover, if the co-extrusion from the die is downwards into a calender roll stack it is possible to obtain very tight tolerance of sheet thickness. Sheet of the laminate, most surprisingly, has good thermoformability characteristics as well as good sealability characteristics. In particular, it is surprising that, although a low melt index would be expected to result in a high thermal retraction, which would make the structural layer difficult to thermoform, the present structural layer has a low thermal retraction.

According to a fifth aspect of the present invention, there is provided a laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt mergibility with said structural layer, having a seal-initiation temperature lower than that of said structural

layer and comprised of a second polyolefin, or an interpolymer thereof, the substance of said structural layer being multi-modal in short chain branching distribution.

According to a sixth aspect of the present invention,
5 there is provided a laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt
10 mergibility with said structural layer, having a seal-initiation temperature lower than the thermoforming temperature plateau of said structural layer and comprised of a second polyolefin, or an interpolymer thereof, the substance of said structural layer being multi-modal in short chain branching distribution.

15 Owing to these two aspects of the invention, an improved laminate can be obtained.

According to a seventh aspect of the present invention, there is provided a laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof,
20 which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt mergibility with said structural layer, having a seal-initiation temperature lower than that of said structural layer and comprised of a second polyolefin, or an
25 interpolymer thereof, said structural layer incorporating a minor amount of a homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin.

According to an eighth aspect of the present invention, there is provided a laminate comprising a structural layer
30 comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt mergibility with said structural layer, having a seal-initiation temperature lower than the thermoforming
35 temperature plateau of said structural layer and comprised of a second polyolefin, or an interpolymer thereof, said structural layer incorporating a minor amount of a homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin.

According to a ninth aspect of the present invention, there is provided a layer comprised of a first polyolefin, or an interpolymers thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and which
5 incorporates a minor amount of a homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin.

According to a tenth aspect of the present invention, there is provided a method comprising a layer comprised of a first polyolefin, or an interpolymers thereof, which is of a
10 low melt index and is multi-modal in molecular weight distribution, and which incorporates a minor amount of a homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin, and thermoforming said layer.

15 Very surprisingly, because homogeneous polyolefins generally are noted for their low melt strength, the incorporation of the homogeneous polyolefin in the (structural) layer improves the thermoformability of the (structural) layer.

20 The layer may be in the form of a monolayer or may be one layer of a laminate. The laminate may include a sealant layer, one or more tie layers, or a barrier layer (such as EVOH or PA); it could also contain additives (such as peelability additives, pigments, UV filters, oxygen
25 scavengers, and anti-microbial agents).

The monolayer or the laminate is preferably of a thickness of at least 100 microns, more preferably of a thickness of at least 200 microns, so that it constitutes sheet rather than film.

30 The melt index of the first polyolefin is preferably lower than 0.8g/10mins., especially lower than 0.45g/10mins., at ASTM D1238-95, Conditions 190/2.16 for HDPE, and preferably lower than 8g/10mins, especially lower than 5g/10mins, at ASTM D1238-95, Conditions 230/2.16 for PP.

35 Most preferably, the substance of the monolayer or the structural layer is multi-modal (e.g. bi-modal) in short chain branching distribution. The first polyolefin may comprise PP, but preferably comprises HDPE of Type III or IV, Category 4 or 5, preferably Category 5, of ASTM D1248-84.

That HDPE has the advantage of having very good impact properties down to temperatures of minus 80°C.

5 The first polyolefin may be modified by incorporating a minor amount of a homogeneous polyolefin which is compatible in melt mergibility with the first polyolefin. The homogeneous polyolefin may be PP or PE where the first polyolefin is PP or HDPE, and is preferably present in an amount of between 2 and 50% by weight, particularly between 10 and 30% by weight. Very surprisingly, because homogeneous
10 polyolefins generally are noted for their low melt strength, this modification improves the thermoformability of the laminate.

The polyolefin of the sealant layer would advantageously comprise PP or PE in the event that the polyolefin of the
15 structural layer comprises PP, or would advantageously comprise PE in the event that the polyolefin of the structural layer comprises HDPE. In the former event, the polyolefin of the sealant layer preferably comprises an interpolymer of PP; in the latter event, it preferably
20 comprises LDPE (low density polyethylene) or LLDPE (linear low density polyethylene) or homogeneous PE or blends thereof, and optionally may include one or more additives, for example a peelability additive, e.g. polybutylene or ionomer.

25 In the case of use of the laminate in a blow-thermoforming process, the sealant layer should have a seal-initiation temperature at least 1°C, preferably at least 5°C, below the thermoforming temperature plateau, preferably the seal-initiation temperature, of the structural layer.

30 Homogeneous polyolefins are polyolefins which, in respect of their compositions and/or manufacture, are best exemplified by Elston in US-A-3645992; Canich in US-A-5026798 and US-A-5055438; Stevens et al. in US-A-5064802; and by the products known as "TAFMER"® available from Mitsui
35 Petrochemical Co. Ltd., "AFFINITY"® and "ENGAGE"® available from The Dow Chemical Company and the metallocene polyethylenes manufactured using the "EXPOL"® process by Exxon Corporation.

The present laminate is particularly, but not

exclusively, applicable to FFS machines.

In order that the invention may be clearly understood and readily carried into effect, an example thereof will now be described.

5 A packaging laminar web is formed by co-extrusion of, in order from the outside to the inside, an HDPE blend [of HDPE (grade reference HDPE 35057E as supplied by The Dow Chemical Company) 86%, "AFFINITY"® PL1880 homogeneous PE 10% and Cabot PE7024 white pigment masterbatch 4% by weight], a PE graft
10 interpolymer tie layer, an EVOH (ethylene vinyl alcohol) barrier layer, a PE graft interpolymer tie layer, and an LDPE blend [of LDPE (grade reference "LACQUTENE" LD0304 as supplied by Atochem) 84% and Shell PB8240 polybutylene 16% for peelability], to provide a laminate of an HDPE blend
15 structural layer 270 microns thick, an outer tie layer 15 microns thick, an EVOH barrier layer 20 microns thick, an inner tie layer 15 microns thick and an LDPE blend sealant layer 30 microns thick.

20 If the EVOH barrier is not required, the outer and inner tie layers and the barrier layer may be omitted, because the HDPE blend readily heat-merges with the LDPE blend (it being generally known that HDPE readily heat-merges with LDPE).

25 Two identical such webs were brought together, sealant layer-to-sealant layer, on a "UNIFILL" TR 86 thermoforming machine and the container outlines sealed at a temperature of 130°C, at which a successful seal was achieved between the sealant layers, and the webs were successfully thermoformed into yoghurt containers of 30cc.

CLAIMS

1. A method comprising providing a laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt mergibility with said structural layer, having a seal-initiation temperature lower than that of said structural layer and comprised of a second polyolefin, or an interpolymer thereof, and thermoforming said laminate.
2. A method comprising providing a laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt mergibility with said structural layer, having a seal-initiation temperature lower than the thermoforming temperature plateau of said structural layer and comprised of a second polyolefin, or an interpolymer thereof, and thermoforming said laminate.
3. A method according to claim 1 or 2, wherein said providing comprises co-extruding the substance to form said structural layer and the substance to form said sealant layer.
4. A method according to claim 3, wherein the co-extrusion from said die is downwards into a calender roll stack.
5. A method according to any preceding claim, wherein said providing comprises blending said first polyolefin, or said interpolymer thereof, with a homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin.
6. A method comprising co-extruding through a flat slot die a first polyolefin, or an interpolymer thereof, which is of low melt index and is multi-modal in molecular weight distribution, and a second polyolefin, or an interpolymer thereof, to provide a laminate comprising a structural layer comprised of said first polyolefin, or said interpolymer thereof, and a sealant layer comprised of said second polyolefin or said interpolymer thereof, having a seal-initiation temperature lower than that of said structural layer and compatible in melt mergibility with said structural

layer.

7. A method comprising co-extruding through a flat slot die a first polyolefin, or an interpolymer thereof, which is of low melt index and is multi-modal in molecular weight distribution, and a second polyolefin, or an interpolymer thereof, to provide a laminate comprising a structural layer comprised of said first polyolefin, or said interpolymer thereof, and a sealant layer comprised of said second polyolefin or said interpolymer thereof, having a seal-initiation temperature lower than the thermoforming temperature plateau of said structural layer and compatible in melt mergibility with said structural layer.

8. A method according to claim 6 or 7, wherein the co-extrusion from said die is downwards into a calender roll stack.

9. A method according to any one of claims 6 to 8 and further comprising, before said co-extruding, blending said first polyolefin, or said interpolymer thereof, with a homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin.

10. A laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt mergibility with said structural layer, having a seal-initiation temperature lower than that of said structural layer and comprised of a second polyolefin, or an interpolymer thereof, said structural layer incorporating a minor amount of a homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin.

11. A laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt mergibility with said structural layer, having a seal-initiation temperature lower than the thermoforming temperature plateau of said structural layer and comprised of a second polyolefin, or an interpolymer thereof, said structural layer incorporating a minor amount of a

homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin.

12. A laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt mergibility with said structural layer, having a seal-initiation temperature lower than that of said structural layer and comprised of a second polyolefin, or an interpolymer thereof, the substance of said structural layer being multi-modal in short chain branching distribution.

13. A laminate comprising a structural layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and a sealant layer compatible in melt mergibility with said structural layer, having a seal-initiation temperature lower than the thermoforming temperature plateau of said structural layer and comprised of a second polyolefin, or an interpolymer thereof, the substance of said structural layer being multi-modal in short chain branching distribution.

14. A laminate according to claim 12 or 13, wherein said structural layer incorporates a minor amount of a homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin.

15. A laminate according to claim 10, 11, or 14, wherein said homogeneous polyolefin is present in said structural layer in an amount of between 2 and 50% by weight.

16. A laminate according to claim 15, wherein said amount is between 10 and 30% by weight.

17. A laminate according to any one of claims 10 to 16, and of a thickness of at least 100 microns.

18. A laminate according to claim 17, and of a thickness of at least 200 microns.

19. A laminate according to any one of claims 10 to 18, wherein said first polyolefin comprises high density polyethylene.

20. A laminate according to claim 19, wherein said high density polyethylene is of Type III or IV, Category 4 or 5,

- of ASTM D1248-84.
21. A laminate according to claim 19 or 20, wherein said high density polyethylene has a melt index lower than 0.8.
22. A laminate according to claim 21, wherein said melt
5 index is lower than 0.45.
23. A laminate according to any one of claims 19 to 22, wherein said second polyolefin comprises polyethylene.
24. A laminate according to claim 23, wherein said second
10 polyolefin is selected from the group consisting of low density polyethylene, linear low density polyethylene, homogeneous polyethylene and blends thereof.
25. A laminate according to any one of claims 10 to 18, wherein said first polyolefin comprises polypropylene.
26. A laminate according to claim 25, wherein said
15 polypropylene has a melt index lower than 8.
27. A laminate according to claim 26, wherein said melt index is lower than 4.
28. A laminate according to any one of claims 25 to 27, wherein said second polyolefin comprises polypropylene.
29. A laminate according to claim 28, wherein said second
20 polyolefin comprises an interpolymer of polypropylene.
30. A layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and which
25 incorporates a minor amount of a homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin.
31. A layer according to claim 30, wherein the substance of said layer is multi-modal in short chain branching distribution.
32. A layer according to claim 30 or 31, wherein said
30 homogeneous polyolefin is present in said layer in an amount of between 2 and 50% by weight.
33. A layer according to claim 32, wherein said amount is between 10 and 30% by weight.
34. A layer according to any one of claims 30 to 33, and of
35 a thickness of at least 100 microns.
35. A layer according to claim 34, and of a thickness of at least 200 microns.
36. A layer according to any one of claims 30 to 35, wherein

said first polyolefin comprises one of polypropylene and high density polyethylene.

37. A layer according to claim 36, wherein said high density polyethylene is of Type III or IV, Category 4 or 5, of ASTM D1248-84.

38. A layer according to claim 36 or 37, wherein said high density polyethylene has a melt index lower than 0.8.

39. A layer according to claim 38, wherein said melt index is lower than 0.45.

40. A laminate according to claim 36, wherein said polypropylene has a melt index lower than 8.

41. A laminate according to claim 40, wherein said melt index is lower than 5.

42. A method comprising providing a layer comprised of a first polyolefin, or an interpolymer thereof, which is of a low melt index and is multi-modal in molecular weight distribution, and which incorporates a minor amount of a homogeneous polyolefin which is compatible in melt mergibility with said first polyolefin, and thermoforming said layer.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 97/01182

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B32B27/32 C08L23/06 C08L23/10 C08J5/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08L C08J B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 95 21743 A (DU PONT CANADA ;BRECK ALAN KEITH (CA); VERDONE ALANA (CA)) 17 August 1995 cited in the application see page 11, line 6 - line 15 see page 11, line 34 - page 12, line 12 see page 17, line 10 - page 19, line 15; claims ---	1
X	FR 2 154 634 A (DU PONT CANADA) 11 May 1973 see claims ---	1
X	US 5 382 631 A (STEHLING FERDINAND C ET AL) 17 January 1995 see column 23, line 38 - column 24, line 48; claims 1,8 ---	1
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

8 January 1998

Date of mailing of the international search report

28/01/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

De Jonge, S

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 97/01182

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>DATABASE WPI Section Ch, Week 7743 Derwent Publications Ltd., London, GB; Class A17, AN 77-76695Y XP002030120 & JP 52 109 580 A (GUNZE LTD) , 13 September 1977 see abstract</p> <p style="text-align: center;">----</p>	1
A	<p>WO 96 16119 A (DOW CHEMICAL CO ;KALE LAWRENCE T (US); JAIN PRADEEP (US); KELLEY D) 30 May 1996 see page 20, line 13 - line 16 see page 21, line 1 - line 13 see claims 1,15,16,18-20</p> <p style="text-align: center;">----</p>	1
X	<p>US 4 339 498 A (WEINER MILTON L) 13 July 1982 see abstract; claims</p> <p style="text-align: center;">----</p>	1
X	<p>US 5 360 648 A (FALLA DANIEL J ET AL) 1 November 1994 see claims</p> <p style="text-align: center;">----</p>	1
X	<p>DATABASE WPI Section Ch, Week 7948 Derwent Publications Ltd., London, GB; Class A17, AN 79-86872B XP002030121 & JP 54 135 875 A (MITSUI TOATSU CHEM INC) , 22 October 1979 see abstract</p> <p style="text-align: center;">----</p>	1
X	<p>EP 0 339 989 A (SHELL OIL CO) 2 November 1989 see claims</p> <p style="text-align: center;">----</p>	1
A	<p>EP 0 517 222 A (HOECHST AG) 9 December 1992 see the whole document</p> <p style="text-align: center;">----</p>	30, 36-38,42
A	<p>EP 0 588 208 A (HOECHST AG) 23 March 1994 see claims; example 1</p> <p style="text-align: center;">----</p>	30,36
A	<p>EP 0 564 206 A (TERUMO CORP) 6 October 1993 see the whole document</p> <p style="text-align: center;">----</p>	30,36
A	<p>EP 0 697 436 A (MONTELL TECHNOLOGY COMPANY BV) 21 February 1996 see claims 1,14</p> <p style="text-align: center;">-----</p>	30,36

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/IB 97/01182

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9521743 A	17-08-95	CA 2182524 A EP 0743902 A	17-08-95 27-11-96
FR 2154634 A	11-05-73	GB 1368634 A BE 789332 A CA 967322 A DE 2247611 A	02-10-74 27-03-73 13-05-75 12-04-73
US 5382631 A	17-01-95	US 5382630 A AT 154060 T AU 615804 B AU 4338089 A CA 1338883 A DE 68928100 D DE 68928100 T DK 132290 A EP 0389611 A JP 3502710 T WO 9003414 A	17-01-95 15-06-97 10-10-91 18-04-90 28-01-97 10-07-97 06-11-97 27-07-90 03-10-90 20-06-91 05-04-90
WO 9616119 A	30-05-96	US 5582923 A AU 4283096 A EP 0792318 A FI 972032 A NO 972203 A	10-12-96 17-06-96 03-09-97 11-07-97 14-07-97
US 4339498 A	13-07-82	US 4275119 A US 4339497 A	23-06-81 13-07-82
US 5360648 A	01-11-94	AU 682526 B AU 7246694 A EP 0705302 A FI 956245 A JP 8511744 T MX 9404784 A WO 9500587 A US 5508051 A	09-10-97 17-01-95 10-04-96 22-12-95 10-12-96 31-01-95 05-01-95 16-04-96
EP 0339989 A	02-11-89	US 4882229 A AT 109814 T	21-11-89 15-08-94

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB 97/01182

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0339989 A		AU 3372589 A DE 68917359 D DE 68917359 T DK 209189 A JP 1315443 A	02-11-89 15-09-94 01-12-94 30-10-89 20-12-89
EP 0517222 A	09-12-92	AT 142672 T CA 2070470 A DE 59207090 D ES 2094255 T US 5338589 A	15-09-96 06-12-92 17-10-96 16-01-97 16-08-94
EP 0588208 A	23-03-94	AU 673368 B AU 4626393 A CA 2105914 A FI 933957 A JP 6179776 A ZA 9306696 A	07-11-96 17-03-94 13-03-94 13-03-94 28-06-94 05-04-94
EP 0564206 A	06-10-93	JP 5293168 A JP 6169972 A JP 6171040 A	09-11-93 21-06-94 21-06-94
EP 0697436 A	21-02-96	IT 1274606 B CA 2155685 A CN 1126733 A JP 8059916 A	18-07-97 10-02-96 17-07-96 05-03-96